

AMINO RESIN

FOR INDUSTRIAL STOVING ENAMELS, ROOM TEMPERATURE ACID CURING CLEAR FOR WOOD COATINGS.
EXCELLENT HARDNESS AND IMPACT RESISTANCE



PRODUCT CODE	%NVM	COLOUR ON GARDNER (@% Solids)	VISCOSITY ON BF @ 25°C	Free formaldehyde (% max)	DESCRIPTION/ USES
LC MF 601	60.0±2.0	1 MAX	800 - 1600 cps	0.5	Butylated melamine formaldehyde resin recommended for industrial baking enamel, can and coil coating paints, acid curing wood coating varnishes. Excellent hardness and impact resistance.
LC UF 501	60.0±2.0	1 MAX	800 - 2000 cps	0.5	Butylated urea formaldehyde resin recommended for industrial baking enamel, acid curing wood coating varnishes. Excellent hardness and impact resistance.