

THERMOPLASTIC ACRYLIC RESIN

FOR GENERAL PURPOSE MASONRY, DECORATIVE COATINGS, AEROSOL PAINTS.TPA EXHIBIT GOOD GLOSS, GOOD COLOUR RETENTION, GOOD OUTDOOR DURABILITY. EXCELLENT SOAP AND DETERGENT RESISTANCE. SUITABLE FOR ROAD MARKING PAINTS



PRODUCT CODE	% NVM (Volatile solvent)	COLOUR ON GARDNER	VISCOSITY ON B4 @ 30°C	ACID VALUE (mg KOH/gm)	DESCRIPTION/ USES
LC TP 850	50.0±2.0 (XL)	1 MAX	40-60 poise	8 Max	Recommended for road marking paints, general purpose masonry, good gloss, colour retention, good outdoor durability, excellent mechanical properties. Excellent soap and detergent resistance
LC TP 851	50.0±2.0 (SN/XL)	1 MAX	50-70 poise	8 Max	Suitable for general purpose masonry, decorative coatings, good gloss, colour retention, good outdoor durability, Excellent soap and detergent resistance
LC TP 852	60.0±2.0 (XL)	1 MAX	250-350 poise	10 Max	Main application for road marking paints, general purpose contraction and decorative coatings, good gloss, good colour retention, good mechanical properties. Excellent solvent, soap, and detergent resistance
LC TP 853	55.0±2.0 (XL)	1 MAX	140-180 poise	10 Max	Recommended for general purpose masonry, decorative coatings, good gloss, colour retention, good outdoor durability. Excellent soap and detergent resistance
LC TP 854	55.0±2.0 (SN)	1 MAX	140-180 poise	10 Max	Recommended for general purpose contraction and decorative coatings, good gloss, colour retention, good outdoor durability. Excellent soap and detergent resistance
LC TP 855	60.0±2.0 (XL)	1 MAX	180-240 poise	10 Max	Main application for road marking paints, general purpose contraction and decorative coatings, good gloss, good colour retention, good mechanical properties. Excellent solvent, soap, and detergent resistance
LC TP 856	65.0±2.0 (BAC)	1 MAX	100-150 poise	8 Max	Suitable for low VOC general purpose contraction and decorative coatings, good gloss, colour retention, good outdoor durability. Excellent mechanical properties. Excellent soap and detergent resistance
LC TP 858	60.0±2.0 (W/S)	1 MAX	60-100 poise	8 Max	Recommended for general purpose contraction and decorative coatings, good gloss, colour retention, good outdoor durability. Excellent soap detergent resistance.