

VINYL ESTER RESIN

IMPROVED POLYESTER IMPROVED VIA BISPHENOL CHLORINATION OR A COMBINATION OF POLYESTER AND EPOXY. CURES, HANDLES, AND PROCESSES LIKE POLYESTER, BUT EXHIBITS HIGHER TEST RESULTS IN CORROSION TEMPERATURE RESISTANCE AND STRENGTH



PRODUCT CODE	APPEARANCE	COLOUR	SOLIDS %	VISCOSITY 25° C (cP)	Gel Time 25° C (min)	Acid Value (mg KOH/g)	HDT	APPLICATIONS
LC 600	Clear	Pale Yellow	60 ± 2	400 ± 100	12 ± 3	10 Max	90 - 100	General Purpose
LC 601	Clear	Pale Yellow	55 ± 2	400 ± 100	15 ± 5	10 Max	90 - 100	Superior Grade
LC 602	Clear	Pale Yellow	60 ± 2	400 ± 100	12 ± 3	10 Max	90 - 100	Fire Retardant