

LONG OIL ALKYD RESIN

DECORATIVE ENAMEL FOR INTERIOR AND EXTERIOR APPLICATIONS. LOW, MEDIUM, AND HIGH VISCOSITY RESINS FOR GOOD PIGMENT WETTING PROPERTIES. HIGH GLOSS, GOOD GLOSS RETENTION, AND GOOD DRYING.



PRODUCT CODE	TYPE OF OIL	%OIL (Approx)	COLOUR ON GARDNER	VISCOSITY ON B4 @ 30°C	A.V. mg KOH/	% NVM	DESCRIPTION/ USES
		%PA (Approx)					
LC A 700	Veg.oil/ Fatty acid	60.0	4 MAX	120+ 20 SEC 50% in W/S	10 MAX	70 ± 2	Very good pigment loading capacity. Good gloss & gloss 70+2 retention, good drying. Decorative enamel for exterior & interior application.
		25.0					
LC A 701	Veg.oil/ Fatty acid	61.0	4 MAX	200+ 20 SEC 50% in W/S	10 MAX	70 ± 2	Good gloss & gloss retention, good drying. Decorative enamel for exterior & interior application.
		25.0					
LC A 702	Veg.oil/ Fatty acid	61.0	4 MAX	240 ± 20 SEC 50% in W/S	10 MAX	70 ± 2	Good gloss & gloss retention, faster drying, good non-yellowing properties. Decorative enamel for exterior & interior application.
		25.0					
LC A 703	Veg.oil/ Fatty acid	60.0	4 MAX	120 ± 20 SEC 40% in W/S	10 MAX	70 ± 2	Good colour & gloss retention, faster drying & high viscosity. Decorative enamel for exterior & interior application.
		25.0					
LC A 704	Veg.oil/ Fatty acid	61.0	4 MAX	180 ± 20 SEC 50% in W/S	10 MAX	80 ± 2	Good pigment loading capacity. Good gloss & gloss retention, good drying. Decorative enamel for exterior & interior application.
		25.0					
LC A 705	Veg.oil/ Fatty acid	65.0	6 MAX	50 ± 20 SEC 50% in W/S	10 MAX	95 ± 2	Good wetting properties & good adhesion. Decorative enamel for exterior & interior application & also use in printing ink.
		24.0					
LC A 709	LINSEED	65.0	8 MAX	120 + 20 SEC 50% in W/S	10 MAX	70 ± 2	Good wetting properties & good adhesion. Decorative enamel for exterior & interior application & also in good quality printing ink.
		24.0					
LC A 710	DCD	61.0	8 MAX	120 ± 20 SEC 50% in W/S	10 MAX	70 ± 2	Very good pigment loading capacity. Good gloss & gloss retention, good drying. Decorative enamel for exterior & interior application.
		25.0					
LC A 712	TALL OIL	61.0	6 MAX	200+ 20 SEC 50% in W/S	10 MAX	70 ± 2	Good gloss & gloss retention, good non-yellowing properties. Decorative enamel for exterior & interior application.
		25.0					
LC A 715	Veg.oil/ Fatty acid	60.0	4 MAX	100+ 20 SEC 40% in W/S	10 MAX	95 ± 2	Good gloss & gloss retention, faster drying & high viscosity. Decorative enamel for exterior & interior application.
		25.0					